



Anti-Crak® HP 58/12

Glass fiber to prevent cracking in concrete and mortar

Anti-Crak® HP fibers are part of the Cem-FIL® product range

PRODUCT DESCRIPTION

Anti-Crak® HP (High Performance) 58/12 is a glass fiber made from AR (Alkali Resistant) glass filaments and engineered to reinforce concrete and mortar against cracking.

Anti-Crak® HP 58/12 has an excellent bond with hydraulic matrices and increases its tensile strength before cracking.

Anti-Crak® HP 58/12 is suitable for all types of concrete formulations and mixing methods due to its specific size, which allows for excellent dispersion of fibers, easy processing, and a very high quality finish.

PRODUCT APPLICATION

Anti-Crak® HP 58/12 was developed to improve resistance against cracking in concrete and mortar. It is mainly used to reinforce **screeds**, and in **residential, commercial, and industrial floor slabs**.



PRODUCT BENEFITS

- Control and prevention of cracking in fresh and hardened concrete and mortar (plastic shrinkage cracking, drying cracking and thermal cracking)
- Improves the durability of mortar and concrete structures
- Improves the mechanical properties of hardened concrete
- Disperses quickly during mixing

- Does not impair concrete pumping
- Allows for high dosages without affecting the workability of the concrete
- Does not require additional water
- Does not corrode
- Easy to handle

FEATURES

- Length: 12 mm
- Aspect ratio (length/diameter): 58
- Density: 2.68 g/cm³
- Modulus of elasticity: 72 GPa
- Size content: 0.8% (ISO 1887)
- Moisture: 0.3% max (ISO 3344)

- Material: Alkali Resistant Glass
- Softening point: 860°C
- Electrical conductivity: Very low
- Chemical resistance: Very high
- Tensile strength: 1,700 MPa



*Our fibers are manufactured with a high zircon content, in compliance with ASTM C1666/C, 1666/M-07, and EN 15422 and under the recommendations of PCI and GRCA

Anti-Crak® HP 58/12

Glass fiber to prevent cracking in concrete and mortar

Anti-Crak® HP fibers are part of the Cem-FIL® product range

USE – DOSAGE

The fibers can be introduced into the skip or mixer at the concrete plant or in the truck mixer on-site. The dosage to use depends on the concrete or mortar formula and desired performance levels. For mortar and concrete, the following dosages are common:

Desired Benefit	No cracking during plastic shrinkage	Replacement of the anti-cracking welded wire mesh
Recommended Dosage	0,3 – 0,6 kg/m ³	0,9 - 1,5 kg/m ³

However, we recommend performing tests to determine the optimum dosage to use for the intended application and desired level of performance.

PACKAGING AND STORAGE

Anti-Crak® HP 58/12 fibers are packaged in individual 600 g and 1 lb water-dispersible bags.

Anti-Crak® HP fibers should be kept in their original packaging and stored away from heat and moisture.

The best storage conditions are:

- Temperature : 15°C – 35°C.
- Moisture : 35 % – 65 %.

QUALITY – CERTIFICATION

- Anti-Crak® HP fibers are manufactured under the ISO 9001 standard quality management system. In addition, the actual performance of Anti-Crak® fibers is subject to independent assessment and approval in Germany (Zulassung no. Z-3.72.1731).
- Anti-Crak® fibers meet the safety standards defined by European Directives 99/45/EC, 67/548/EEC, and their latest amendment.

Cem-FIL® Customer Service

Alcala de Henares, Spain
Tel. : + 34.91 885 58 03
Fax : + 34.91 885 58 34
Cem-fil@owenscorning.com

WWW.CEM-FIL.COM



OCV™ Reinforcements

**OWENS CORNING
COMPOSITE MATERIALS, LLC**
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1.800.GET.PINK™
www.owenscorning.com
www.ocvreinforcements.com

**EUROPEAN OWENS CORNING
FIBERGLAS, SPRL.**
166, CHAUSSÉE DE LA HULPE
B-1170 BRUSSELS
BELGIUM
+32.2.674.82.11

OWENS CORNING – OCV ASIA PACIFIC
SHANGHAI REGIONAL HEADQUARTERS.
2F OLIVE LVO. MANSION
620 HUA SHAN ROAD
SHANGHAI 200040
CHINA
86.21.62489922

Les informations et données qui figurent dans ce document sont uniquement remises pour faciliter la sélection d'un renfort. Les renseignements que contient cette publication sont basés sur des données réelles obtenues en laboratoire et sur le terrain, par l'expérience de nos essais. Nous croyons ces informations fiables mais nous ne garantissons pas leur convenance au procédé de l'utilisateur, ni nous n'assumons de responsabilité résultant de leur utilisation ou performance. Avant la phase de production, l'utilisateur s'engage à procéder à des essais approfondis pour chaque application afin de déterminer si elle convient. Il est important pour l'utilisateur de déterminer les propriétés de ses propres composés commerciaux lors de l'utilisation de ce renfort ou de tout autre. Du fait des nombreux facteurs qui influencent les résultats, nous n'offrons aucune garantie de quelque nature que ce soit, ni expresse ni tacite, y compris celles de la qualité marchande et de l'adaptation à un usage spécifique. Les déclarations figurant dans ce document ne doivent pas être considérées comme étant des engagements ou des garanties ou comme des encouragements à ne pas respecter un brevet ou à commettre une infraction par rapport à une loi, un code de sécurité ou une règle d'assurance.

Pub. No. 10013671-A. Owens Corning reserves the right to modify this document without prior notice. ©2011 Owens Corning

Cemfil_5812_ww_01_2011_Rev0_EN